



CEMENTATION STEEL

Internal designation	EUROPE EN	ITALY UNI	SPAIN UNE	GERMANY DIN	FRANCE AFNOR	U.K B.S.	SWEDEN SS	USA AISI SAE
C10	C10E C10R	C10	F1510	Ck15 1.1121	XC10	045M10	1265	1010
C15	C15E C15R	C15	F1511	Ck15 1.1141 Cm15 1.1140	XC12	--	1370	1015
XC18	C16E	C20	F1511	Ck22 1.1151 Cm22 1.1149	XC18	070M20	1313	A29 1016
16MnCr5	16MnCr5	16MnCr5	F1516	16MnCr5 1.7131	16MC5	--	2173	5115
20MnCr5	20MnCr5	20MnCr5	F150.D	20MnCr5 1.7147	20MC5	--	--	5120
17NiCrMo6-4	17NiCrMo6-4	--	--	17NiCrMo64	--	--	--	--
18NiCrMo5	17NiCrMo6-4	18NiCrMo5	--	--	18NCD6	815M17	2523	4317
20NiCrMo2-2	20NiCrMo2-2	20NiCrMo2	F1522	21NiCrMo2 1.6523	20NcD2	805M20	2506	8620 appr.
16CrNi4	16NiCr4	16CrNi4	F1581	15CrNi6 1.5919	16NC4	637M17	2511	3215 appr.
16NiCr11	16NiCr12	16NiCr11	F154 F150.I	14NiCr10 1.5732	16NC11	--	--	3415
16NiCrMo12	14NiCrMo13-4	16NiCrMo12	--	--	16NCD13	--	--	9314